



DATA SHEET

ELECTROSHIELD

Laminates and Coated Products Engineered
to Solve EMI/RFI Shielding Problems

PRODUCT: A-25

CONSTRUCTION: .00035" aluminum foil
.002" polyester film

APPLICATION: EMI and FRI shielding of electronic components

<u>PROPERTY</u>	<u>VALUE</u>	<u>TEST METHOD</u>
Signal Attenuation:	95 dB @ 100 MHz	ASTM D4935-99
Dielectric Strength:	8,800 volts	ASTM D149
Thickness:	.0025" +/- 10%	PSTC-33
Peel Strength:	N/A	
Tensile Strength:	14,500 P.S.I.	ASTM-D-882
Elongation at Break:	90%	ASTM-D-882
Color:	Silver	
Shelf Life:	1 year when stored under conditions of 70 degrees F. (21 degrees C.) and 50% R.H.	

P/N 414

rev2: 07/18/07

Values are not intended for Engineering Specifications. Before using, user shall determine the suitability of the product for his intended use, and user assumes all risk and liability whatsoever in connection therewith.

Seller assumes no liability beyond the replacement value of material.

•Manufacturers of Flexible
Laminated and Coated Products.
Fabrics.

•Electrical and Electronic Shielding
and insulation Composites.

•Specialty Pressure Sensitive Tapes-
Laminates-Films, Foils, Papers,