



DATA SHEET

ELECTROSHIELD

Laminates and Coated Products Engineered
to Solve EMI/RFI Shielding Problems

PRODUCT: A-55-PS

CONSTRUCTION: .00035" aluminum foil
.005" polyester film
.0015" acrylic pressure sensitive adhesive
90 lb. release liner

APPLICATION: EMI and RFI shielding of electronic components

SPECIFICATION: FCC part is sub-part J. Vol. 11, July 1981

<u>PROPERTY</u>	<u>VALUE</u>	<u>TEST METHOD</u>
Thickness:	.0070" +/- 5%	ASTM-D-3652
Peel Strength:	40 oz./inch of width	ASTM-D-1000
Tensile Strength:	18,000 P.S.I. min.	ASTM-D-882
Elongation at Break:	115%	ASTM-D-882
Color:	Silver	
Shelf Life:	1 year when stored under conditions of 70 degrees F. (21 degrees C.) and 50% R.H.	

P/N 422

date 07/21/94

*Values are not intended for Engineering Specifications. Before using, user shall determine the suitability of the product for his intended use, and user assumes all risk and liability whatsoever in connection therewith.
Seller assumes no liability beyond the replacement value of material.*

•Manufacturers of Flexible
Laminated and Coated Products.
Fabrics.

•Electrical and Electronic Shielding
and insulation Composites.

•Specialty Pressure Sensitive Tapes-
Laminates-Films, Foils, Papers,